



Bancroft Soft Furnishings LTD
Block D Unit 3
Chamberhall Business Park
Harvard Road
Bury, BL9 0FU
Great Britain

Your notice of
12-05-2023

Your reference

Date
21-05-2024

Analysis Report 23.02730.12

Modification

Required tests :

EN 13773 (2003)

Sample id	Updated information given by the client	Date of receipt
T2311633	7067R Eclipse Recycled FR fabric	12-05-2023

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Samples

T2311633
7067R Eclipse Recycled FR fabric





Reference: T2311633 - 7067R Eclipse Recycled FR fabric

Washing and drying

Date of ending the test	16-05-2023
Standard used	ISO 6330 (2021)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	3N- 30°C (2021)
Drying method	A = Line dry (2021)
Number of washing cycles	3
Mass of the test specimens	1505g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2311633_01d



Reference: T2311633_01d - 7067R Eclipse Recycled FR fabric

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test	22-05-2023
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)

Deviation from the standard -

Conditioning	20°C, relative humidity 65%
Testing atmosphere	23°C, relative humidity 53%

Ignition Bottom edge

The test specimens have been washed 3 times instead of 12 times.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	3
4	2	1
5	0	1
6	0	2
7	1	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
 The test requires at least five instances of ignition and five instances of non-ignition.
 Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
 No ignition within 20 s

Reference: T2311633_01d - 7067R Eclipse Recycled FR fabric

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 22-05-2023
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 3 times instead of 12 times.

Length

	Front	Back	Front	Front
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	130	135	135
Flaming debris	no	no	no	no

Width

	Front	Back	Back	Back
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	135	130	130
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1